

Résearch and Development Technical Report Report ECOM- 72-0061-11

AD A O 44077

THIN FILM TRANSISTOR-ADDRESSED DISPLAY DEVICE

T. P. Brody

F. C. Luo

D. H. Davies

E. W. Greeneich

WESTINGHOUSE ELECTRIC CORPORATION Research Laboratories Pittsburgh, Pennsylvania 15235

August, 1977

CA PROPER

Eleventh Quarterly Report for Period - September 1976 - December 1976

DISTRIBUTION STATEMENT
Approved for public release; distribution unlimited

ECOM

US ARMY ELECTRONICS COMMAND FORT MONMOUTH, NEW JERSEY 07703

NOTICES


DISCLAIMERS

The findings in this report are not to be construed as an official Department of the Army position, unless so designated by other authorized documents.

The citation of trade names and names of manufacturers in this report is not to be construed as official Government endorsement or approval of commercial products or services referenced herein.

DISPOSITION

Destroy this report when it is no longer needed. Do not return it to the originator.



THIN FILM TRANSISTOR-ADDRESSED DISPLAY DEVICE

T. P. Brody, F. C. Luo, D. H. Davies, E. W. Greeneich

August, 1977

Contract No. DAABO7-72-C-0061

Eleventh Quarterly Report for Period September 1976 - December 1976



SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

REPORT DOCUMENTATION PAGE	READ INSTRUCTIONS BEFORE COMPLETING FORM
REPORT NUMBER (9) 2. GOVT ACCESSION	NO. 3. RECIPIENT'S CATALOG NUMBER
ECOM-72-0061-11	(9)
FITLE (and Subtitle)	5. TYPE OF REPORT & PERIOD COVERED
6)	11th Quarterly Report 10.1
Thin Film Transistor Addressed Display Device,	Sep — Dec 1976,
	77-9F9-DSPLA-R2
AUTHOR(s)	8. CONTRACT OR GRANT NUMBER(S)
	(3)
Thomas P. Brody, Fang C./Luo, David H./Davies, Edwin W./Greeneich	DAAB07-72-C-0061
PERFORMING ORGANI ATION NAME AND ADDRESS	10. PROGRAM ELEMENT, PROJECT, TASK. AREA & WORK UNIT NUMBERS
Westinghouse Research Laboratories	Project No.
Pittsburgh, Pennsylvania, 15235 376	1S7 62705-AH94-D105
1 CONTROLLING OFFICE NAME AND ADDRESS	12. REPORT DATE
US Army Electronics Command	August , 1977
DRSEL TL BD Fort Monmouth NJ	13. NUMBER OF PAGES
4 MONITORING AGENCY NAME & ADDRESS(if different from Controlling Offi	
	Unclassified
16) 15762705 AH 94	
(17)	15a. DECLASSIFICATION DOWNGRADING
1 D195	
7 DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if differen	nt from Report)
8 SUPPLEMENTARY NOTES	
1	
9 KEY WORDS (Continue on reverse side if necessary and identify by block nu	mber)
display transistors	
	in.
display transistors electroluminescence matrix	in.
display transistors electroluminescence matrix thin films	À
display transistors electroluminescence matrix thin films AGSTRACT (Continue on reverse side it necessary and identify by block num This is the eleventh quarterly report on Contra	nter) act DAAB07-72-0061.
display transistors electroluminescence matrix thin films ABSTRACT (Continue on reverse side it necessary and identify by block num This is the eleventh quarterly report on Contra During this period we have improved the quality	nct DAAB07-72-0061.
display transistors electroluminescence matrix thin films ABSTRACT (Continue on reverse side if necessary and identify by block num This is the eleventh quarterly report on Contra During this period we have improved the quality TFT-EL displays. In addition we have rebuilt to	nct DAAB07-72-0061. The level of the 60 x 60 30 lpiche jigs and tooling and
display transistors electroluminescence matrix thin films ABSTRACT (Continue on reverse side if necessary and identify by block num This is the eleventh quarterly report on Contra During this period we have improved the quality TFT-EL displays. In addition we have rebuilt t fabricated 30 lpi displays using a new format.	nect DAAB07-72-0061. The level of the 6 x 6 30 1pi The jigs and tooling and This format was designed
display transistors electroluminescence matrix thin films O ABSTRACT (Continue on reverse side if necessary and identify by block num This is the eleventh quarterly report on Contra During this period we have improved the quality TFT-EL displays. In addition we have rebuilt t fabricated 30 lpi displays using a new format. to be compatible with the ECOM-ARTADS Digital M	nect DAAB07-72-0061. The level of the 6 x 6 30 1pi The jigs and tooling and This format was designed Message Device. A few runs
display transistors electroluminescence matrix thin films ABSTRACT (Continue on reverse side if necessary and identify by block num This is the eleventh quarterly report on Contra During this period we have improved the quality TFT-EL displays. In addition we have rebuilt t fabricated 30 lpi displays using a new format.	nect DAAB07-72-0061. The level of the 6 ^D x 6 ^D 30 1pi The jigs and tooling and This format was designed Message Device. A few runs

DD 1 JAN 73 1473 EDITION OF 1 NOV 65 IS OBSOLETE

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

TABLE OF CONTENTS

		PAGE
,	Introduction	1
1.	Introduction	1
2.	Improved deposition methods for enchanced thin-film circuit fabrication	2
3.	Development of a reliable second-level electroding process	3
4.	Translation of process to alternate format	7
5.	Results achieved with new format	12
6.	Considerations regarding display life	15
7.	Conclusions	22
8.	Anticipated results next quarter	22
9.	Contributing personnel	22
0.	Publications, reports, conferences, lectures, etc	23

LIST OF ILLUSTRATIONS

		Page
1.	Microscopic defect site in thin film circuit	4
2.	Improved level of operation in 6" x 6", 30 lpi 2 level electroded TFT-EL display	5
3.	Dark field photomicrograph of residual defect causing species	6
4.	Second level output pad; contact failure	8
5.	Format of new display	10
6.	New cell layout used in X-Y display fabrication	11
7.	Operational performance level achieved in DMD format	13
8.	New elemental cell layout as actually fabricated	14
9.	Phosphor life relationship	16
10.	Period of TFT multivibrator circuit vs elapsed time under continuous operation	20
11.	Device I/V characteristics before and after	21

1. Introduction

Up to this reporting period we have demonstrated the following:

- Excellent, near defect free, thin film transistor addressed electroluminescent (TFT-EL) displays at 20 lines per inch, 6" x6".
- Reasonable quality TFT-EL displays at 30 lines per inch, 6" x 6".
- A process to increase the elemental lit area per cell to >70%.
- The achievement of drift-free stable high voltage, low leakage TFTs. In this report we will discuss the continuation of the 6" x 6", 30 lines per inch work; the achieving of good quality (low defect count) displays that utilize a reliable second-level output electroding process is detailed. In addition we report on the modification of the technique that alters the format to a design that allows direct compatability with an existing Army TACFIRE system component, the ARTADS-Magnavox Digital Message Device (DMD). A convincing demonstration of the wide format universality of the concepts was achieved; within a very few fabrication runs reasonable quality DMD configured displays were made

Further, the design of the elemental cell thin film layout in this DMD configured display was made compatible with alternate production-type processes. This indicates that all other factors being equal it should be possible to fabricate such displays with methods more amenable to mass-production methods. Finally the results of a continuing TFT test program are given. The test now has accumulated over 20,000 hrs.

of continuous operation with only a minor change in TFT threshold that has no significant impact on display operation. Projections from the data indicate that we could expect >200,000 hrs. of operation (25 yrs) and still be well within the allowable transistor threshold operational range.

2. Improved Deposition Methods for Enhanced Thin Film Circuit Fabrication

Major improvements were previously achieved in the display defect count through improved substrate and mask cleanliness. Further refinements in these processes failed to significantly further improve the defect level. Yet detailed tracing of individual defects (elements on or off uncontrolled by the bias levels, shorted busbar crossovers and "opens" in the thin film circuits) indicated that particulate contaminants were still evident in the films at each defect spot. Analysis has indicated that a partial cause of these is "in-system" particulates, i.e. metal flakes generated in the vacuum system itself due to films peeling off the walls and jig surfaces. The particulates settle and are not significant during operation but are swirled through the chamber during roughing, (the initial chamber evacuation by the rotary pump). To eliminate these we have adopted a procedure whereby the mask X-Y set is closed and the substrate clamped to it during this roughing procedure. This seals the mask and substrate surfaces and prevents particulate pick up. Although this procedure has helped it was found not to be a complete answer. The film quality still needed improvement, black irregular inclusions still existed in both metal and

dielectric films. Fig (1) illustrates some of these microscopic defects. The species shown, although small, are still sufficient to cause shorting in the component. After much experimentation we have now achieved a significant reduction in this problem through more effective degassing of the source materials, more uniform sweep on the e-beam gun and the use of a modified e-beam gun; the AIRCO ST1H-2A. The new gun incorporates a rotating hearth surround rather than a static one and this has helped. Fig (2) illustrates a typical 6" x 6" 30 lpi display in operation. The quality level has improved since the last period although further advances are required. We have examined and traced individual defects in these latest displays. On first examination the bulk of the defect causing particulates, such as shown in Fig (1), have been removed. However we have examined such circuits in a high power dark field microscope. Under these conditions it is clear that we still have a particulate defect problem but now we are dealing with a small class of particles. Fig (3) illustrates these sub-micron level defect species in dark field microscopy.

3. Development of a Reliable Second-Level Electroding Process

We use a laminar resist as an insulation layer and to provide isolation between a top electrode and the thin film transistor circuits. This multi-layer approach was perfected in previous months, however, test operation indicated that some first to second level contacts were not reliable. The failure mode leaves the original output pad still lit thereby indicating the elemental circuit is still functional but




Fig. 1. Microscopic Defect Site in Thin Film Circuit

```
DISPLAY *TFT*EL* DISPLATED BY A TENT OF THE CONTROL OF THE CONTROL
```

Fig. 2. Improved Level of Operation in 6" x 6", 30 lpi 2 Level Electroded TFT-EL Display




Fig. 3. Dark Field Photomicrograph of Residual Defect Causing Species

examination revealed that the photoresist was lifting and breaking the contact. After several attempts a process that post-hardens the resist at the contact interface with the glass was developed. Reverse exposure with long wavelength ultraviolet is used; the EL output contact pad of the TFT elemental circuits being used as the self-aligning 'photomask."

This process appears to work very well, since incorporation we have not seen evidence of first to second level failure.

4. Translation of Process to Alternate Format

As a result of a contract modification the process was now adapted to change the format of the display from 6" x 6" to 3.4" x 7.0" $(2.9" \times 6.6" \text{ active})$. This latter format is compatible with the Magnavox Corporation's-ARTADS Digital Message Device (DMD). It was decided that no basic elemental circuit changes were needed and the same thin film material system would be used. The display is 8 x 32 characters (256) or 77 x 222 lines when fully populated. The elemental resolution is there \sim 30 lpi, close to what was being fabricated at $6" \times 6"$.

It was determined that the following actions were required to implement this change.

- (1) Jig modifications needed
 - (a) Notch out interior plates for new area
 - (b) New substrate holder for new format



Fig. 4. Second Level Output Pad; Contact Failure

- (c) New mask holder
- (d) New magnet holder
- (2) New X-Y masks for circuit fabrication needed. It was decided that these would be exactly to the required format but should have extra lines for flexibility and be on the required 750 μ m/950 μ m basis.
- (3) New edge connector masks needed. Must pick up alternate contacts to pull out source and ground in appropriate direction.
- (4) Riston process. It was decided to generate a new photoplate via metal master and contact print as needed.
- (5) New glass substrates needed. They can be provided by Corning Glass.

All these tasks have been achieved and the new jig is in use. No significant problems were met except for the edge contact. The picking out of the contacts with each separate block in different directions was difficult. Several new methods are being tried. Meanwhile initial displays were made with "single edge" source and gate contacts.

The overall design for the new display is shown in Fig (5). The elemental resolutions are 750 μm in the horizontal and 950 μm in the vertical. The active display area is 2.9" x 6.6" and the display has 225 x 80 lines, all 17,920 elements are addressable. A \sim 0.25" edge contact border surrounds the active area.




Fig. 5. Format of New Display




Fig. 6. New Cell Layout Used in X-Y Display Fabrication

5. Results Achieved with New Format

After very few runs displays were made with reasonable performance levels; although not perfect the displays are a convincing demonstration of the ease of translation to a new format. Fig. (7) illustrates the results. Note that the elemental electrical circuit is identical to that used previously as is the material system. Some changes were made in the individual thin film layouts however. The reason for these changes were two-fold.

- (a) Through more detailed examination of layout tolerances, design rules etc. developed over several years of experience, it was felt that a single-level display could be made with this fermat without significant sacrifice in the percent lit area. This is both simpler to make and possibly could have better life since it excludes the potentially sensitive Riston (R) layer being overlaid with a top electrode.
- (b) It was decided to utilize a layout that was appropriate from a future 'production' standpoint. A production process would most likely require a dedicated mask system rather than an X-Y method. This in turn requires a computer aided design system (e.g. Applicon (R)), computer controlled photoplate pattern generators and complex patterned masks. These constraints result in a complex set of design rules that limit layout designs. In association with Contract DAABO7-76-C-0027 a detailed design base following those rules has been obtained and the X-Y layout used in this program was based on those rules. Fig (8) shows the optimum layout as actually fabricated. As can be seen from Fig (7) successful displays have been made in this format; further improvements are expected as more attempts are made at this format.



Fig. 7. Operational Performance Level Achieved in DMD Format




Fig. 8. New Elemental Cell Layout As Actually Fabricated

6. Considerations Regarding Display Life

The factors raised by life requirements can be divided into three principal areas.

- 1. Brightness deterioration that will occur with operation.
- Defects that could occur, elements or lines turning on or off and not being controllable. These could arise because of shorts or opens in the circuit.
- 3. Changes in the TFT properties with operation that could cause the elements to drift out of specification. This applies to the circuit plate somewhat but is more significant if we wish to pursue integrated peripheral scanning circuits.

We are confident that we can satisfy these conditions for the following reasons.

The change in EL brightness with operating life is known and definable under comparable drive and process conditions to those required here. Half lives of >5000 hr have been observed with this fabrication method, the phosphor following the slow decay relationship shown in Fig.(9). This figure is a revision of prior data where a somewhat longer half life was indicated. Recent results have shown that life is strongly dependent on the method of forming the EL layer. Using a brush type approach to phosphor deposition results in a higher phosphor/binder ratio. The result is that the embedded phosphor layer has somewhat longer life than if a high binder content is present.

^{*}Quarterly Report #4.




Fig. 9. Phosphor Life Relationship

The method now used to fabricate displays (spray) results in a higher binder ratio in the eventual layer. We have discovered, therefore, that a more realistic figure for a half-life for phosphor layers prepared in the same fashion as the display is $\sim 6,000$ hr (see Fig. (9)). Two factors alleviate this condition somewhat:

- 1. We are attempting to review our phosphor layer deposition method to incorporate the better methods used in the earlier life tests. This includes silk screening of the phosphor rather than spraying it and also includes the incorporation of a thin (800 $\overset{\circ}{A}$) dielectric film over the phosphor. The latter prevents lateral leakage and can be used to enhance contrast.
- 2. It is possible to still meet, with adequate leeway, good operational life times. Using the relationship of Fig (9) and the phosphor voltage/brightness relationship, it is possible to convert a 1000 hr requirement (say) into drive voltage. We have determined that 40 fL is more than sufficient to meet 2000 fc legibility. To be able to achieve this after say 1000 hr requires that the matrix circuit be capable of handling a drive voltage equivalent to L_1 , where L_1 is derived from the value of (L_1/L_0-1) . When t=1000 hr in Fig (9) this is ~ 0.40 . Therefore $L_1/L_0=1.40$ and since $L_0=40$ fL, then $L_1=56$ fL and the required voltage drive condition is ~ 90 V rms is only marginally above the initial drive requirement of 80 V rms and is well within the capability of the matrix and TFTs. This surprisingly small increase in the maximum voltage rating comes about because of the superlinear brightness/voltage relationship inherent in EL phosphor.

The question of TFT matrix "life" is well documented and reference is made 1,2 to previous publications on this topic. Two major factors are important: the appearance of defects (related to matrix shorting) and device drift. Two classes of defects are present in the display -- initial defects and those that appear during life. The former are counted as scrap and are not, therefore, under consideration. The latter we have found come under two categories: those which appear in the first few hours of operation due to poor quality crossovers or devices and those which appear during regular operation. Our experience is that the vast majority of defects appear during the first few hours of life. After this it is relatively rare to observe a defect appearing if the voltage used in the initial burn-in is not exceeded. This phenomenon, called "infant mortality," is common to all integrated circuitry. Based on this, we conduct a 2-hr burn-in at the maximum voltage rating after each display is fabricated. A failure here is considered part of fabrication yield, not life. (The question of initial "as fabricated" defects is discussed in Section (2) above).

Transistor threshold drift is a phenomenon that does occur, as indeed it occurs with all silicon MOSFET transistors. With regard to the matrix transistors, it is of relatively little significance, as has been discussed previously. The effect of drift on alphanumeric or other non-gray level displays is minimal since the devices are operating in a saturation mode. However, this is not the case for the pheripheral scanning circuits. To test stability, in a mode not significantly different from the operation of the scanning circuits, the following test was conducted.

The test circuit for this study was a free-running astable multivibrator that was discussed in detail in the Ninth Quarterly Report.

Prior to the start of the test, curve tracer I-V characteristics were obtained on device T_1 . The circuit was then started and left to run continuously. The LED flashes at roughly a 1 Hz rate, and periodic data was obtained simply by measuring (with a stopwatch) the time required to generate 100 pulses. The data are shown in Fig (10). After 20,000 hr of operation, I-V characteristics were again taken on T_1 , which were very nearly identical to the original set except for a slight shrinking due to a small shift in threshold voltage (approximately 0.3V) as a result of slow electronic trapping. There is no evidence of fast trapping as indicated by the equivalent of pulsed-mode characteristics and dc characteristics.

The change in the pulse period after 20,000 hr of continuous operation was 15% and can be attributed to the shift in $V_{\rm T}$. This change in $V_{\rm T}$ with time is essentially logarithmic, so we would expect another 15% shift after 200,000 hr (25 years). The I-V characteristics before and after the test are shown in Fig. (11).

These minor changes in V_T are not significant in the operation of the display or indeed the scanning circuit. It is clear, therefore, that the technology can satisfy, say, a 1000 hr life requirement. To be sure, we cannot at this stage point to extensive life data on existing displays. Such experiments are being set up now as part of the present MMLTE program.

† Initial data on 6 × 6 in. displays indicates

USA ECOM Contract DAABO6-76-C-0027




Fig. 10. Period of TFT Multivibrator Circuit vs. Elapsed Time Under Continuous Operation




Fig. 11. Device I/V Characteristics Before and After 20,000 hr. Test

good potential. Over 100 hr of noncontinuous operation on a 6 in., 20 lines/inc. display has been obtained without a significant matrix defect occurring.

Conclusions

- 1. The extension of the previously proven $6" \times 6"$ 20 lpi technology to 30 lpi is now well established and good quality displays were made in this period.
- The second level electroding process to increase the percent lit area is now reliable.
- 3. The methods have also been reconfigured under a contract modification and displays compatible with an Army field terminal (the ARTADS-DMD) fabricated.

8. Anticipated Results Next Quarter

- Several good quality DMD formatted displays fabricated using X-Y method.
- Displays rigorously tested for performance, life, and environmental properties.
- First attempt at integration of DMD display with the compatible thin film scanning circuit recently developed under Westinghouse support.

9. Contributing Personnel

Dr. T. P. Brody

Dr. Z. P. Szepesi

D. W. Yanda*

Dr. D. H. Davies*

Dr. E. W. Greeneich

D. Leksell*

Dr. F. C. Luo*

W. A. Hester*

^{*}Those persons indicated worked essentially full time on the Contract ($\sim 400 \text{ hrs}$).

9. Publications, Reports, Conferences and Lectures

The following paper was presented

"Real Time Video Performance on TFT-EL Displays" by T. P. Brody, F. C. Luo, Z. P. Szepesi, D. H. Davies, P. Kennedy, AGED/IEEE and Soc. of Info. Display, Joint Biennial Conference, NY, 1976.

Although the work reported was principally supported by Westinghouse this program reported here was also a contributory factor and was so acknowledged.

BEST_AVAILABLE COPY

DISTRIBUTION LIST

COMMANDER NAVAL ELECTRONICS LABORATORY CENTER ATTN: LIBRARY SAN DIEGO, CA 92:52	CDR, NAVAL SURFACE WEAPONS CENTER WHITE DAK LABORATORY ATTN: LIBRARY, CODE WX-21 SILVER SPRING, MD 20910	COMMANDANT, MARINE CORPS HQ, US MARINE CORPS ATTN: CODE LMC WASHINGTON, DC 20380	HO, US MARINE CORPS ATTN: CODE INTS WASHINGTON, DC 20380	COMMAND, CONTROL & COMMUNICATIONS DIV DEVELOPMENT CENTER MARINE CORPS DEVELOPMENT & EDUC COMD AUANTICO, VA 22134	ROME AIR DEVELOPMENT CENTER ATTN: DOCUMENTS LIBRARY (TILD) GRIFFISS AFB, NY 13441
206	207	210	211	212	301
DEFENSE DUCUMENTATION CENTER ATTN: DOCTCA CAMERON STATION (BLDG5) ALEXANDRIA, VA 22314	CODE R123* TECH LIBRARY DCA DEFENSE COMM ENGRG CTR 1860 WIEHLE AVE RESTON* VA 22090	DEFENSE COMMUNICATIONS AGENCY TECHNICAL LIBRARY CENTER CODE 205 (P. A. TOLOVI) WASHINGTON, DC 20305	OFFICE OF NAVAL RESEARCH CODE 427 ARLINGTON® VA 22217	GIDEP ENGINEERING & SUPPORT DEPT TE SECTION PO BOX 398 NORCOM CA 91760	DIRECTOR NAVAL RESEARCH LABORATORY ATTN: CODE 2627 WASHINGTON, DC 20375
101	103	104	200	203	205

Electronic to 2 coulds if report is not released; to public. See Mires 70-31 for types of

BEST AVAILABLE COPY

COMMANDANT US ARMY MILITARY POLICE SCHOOL ATTN: ATSJ-CO-M-C FORT MCCLELLAN, AL 36201	COMMANDER US ARMY INTELLIGENCE CENTER & SCHOOL ATTN: ATSI-CO-MD FORT HUACHUCA: AZ 85613	COMMANDER HG FORT HUACHUCA ATTN: TECHNICAL REFERENCE DIV FORT HUACHUCA: AZ 85613	COMMANDER US ARMY ELECTRONIC PROVING GROUND ATTN: STEEP-MI FORT HUACHUCA! AZ 85613	COMMANDER USASA TEST & EVALUATION CENTER ATTN: IAO*CDR*T FORT HUACHUCA! AZ 85613	COMMANDER HQ US ARMY COMMUNICATIONS COMMAND ATTN: CC-OPS-SM FORT HUACHUCA, A7 85613	DEPUTY FOR SCIENCE & TECHNOLOGY OFFICE, ASSIST SEC ARMY (R&D) WASHINGTON, DC 20310
408	417	418	002	420	421	437
HQ ESD (DRI) L. G. HANSCOM AFB BEDFORD, MA 01731	HQ, AIR FORCE SYSTEMS COMMAND ATTN: DLCA ANDREWS AFB WASHINGTON, DC 20331	CDR, US ARMY MISSILE COMMAND REDSTONE SCIENTIFIC INFO CENTER ATTN: CHIEF, DOCUMENT SECTION REDSTONE ARSENAL, AL 35809	COMMANDER US ARMY MISSILE COMMAND ATTN: DRSMI*RE (MR. PITTMAN) REDSTONE ARSENAL, AL 35809	COMMANDER US ARMY AEROMEDICAL RESEARCH LAR ATTN: LIBRARY FORT RUCKER, AL 36362	COMMANDANT US ARMY AVIATION CENTER ATTN: ATZQ-D-MA FORT RUCKER, AL 36362	DIRECTOR, BALLISTIC MISSILE DEFENCE ADVANCED TECHNOLOGY CENTER ATTN: ATC-R, PD 80x 1500 HUNTSVILLE, AL 35807
307	314	403	404	405	406	001

DIRECTOR US ARMY MATERIEL SYSTEMS ANALYSIS ACTY ATTN: DRXSY=T		COMMANDER US ARMY TANK-AUTOMOTIVE COMMAND ATTN: DOLTED		CDR. US ARMY AVIATION SYSTEMS COMMAND ATTN: DRSAV-G		COMMANDER, PICATINNY ARSENAL ATTN: SARPA-FR-S		COMMANDER PICATINNY ARSENAL		COMMANDER PICATINNY ARSENAL	DOVER NJ 07801	PROJECT MANAGER, REMBASS ATTN: DRCPM-RBS FORT MONMOUTH, NJ 07703
482	001	466	001	507	001	511	002	512	001	513	001	515
											ARMY	
HGDACDAMATARP/DR, F. D. VERDERAME) WASHINGTON, DC 20310	COMMANDANT US ARMY SIGNAL SCHOOL	ATTN: ATSN-CTD-MS FORT GORDON: GA 30905	DIRECTOR OF COMBAT DEVELOPMENTS US ARMY ARMOR CENTER	ATTN: ATZK-CD-MS FORT KNOX: KY 40121	(US ARMY DRDNANCE SCHOOL ATIN: ATSL-CO-OR ABERDEEN PROVING GROUND, MD 21005		2800 POWDER MILL ROAD ADELPHI, MD 20783	IRECTOR SALLICATE		DIAMOND LABORAT	ATINI DHXDU-HUB (DK. J. NEMAKICH) 2800 POWDER MILL ROAD ADELPHI, MD 20783
438	455	001	470	005	473	005	475	001	477	001	481	001

COMMANDANT US ARMY AIR DEFENSE SCHOOL ATTN: ATSA-CD-MC FORT BLISS, TX 79916	COMMANDER US ARMY NUCLEAR AGENCY FORT BLISS, TX 79916	COMMANDER, HO MASSTER TECHNICAL INFORMATION CENTER ATTN: MRS. RUTH REYNOLDS FORT HOOD! TX 76544	COMMANDER, DARCOM ATTN: DRCDE 5001 EISENHOWER AVE ALEXANDRIA, VA 22333	CDR, US ARMY SECURITY AGENCY ATTN: IARDA-IT ARLINGTON HALL STATION ARLINGTON, VA 22212	COMMANDER US ARMY MOBILITY EAP RES & DEV CAATTN: DRXFB-R FORT BELVOIR, VA 22060	COMMANDER US ARMY ENGINEER TOPOGRAPHIC LAB ATTN: ETL-TD-EA FORT BELVOIR, VA 22060
554	555	556	563	564	568	569
COMMANDER US ARMY SATELLITE COMMUNICATIONS AGCY ATTN: DRCPM-SC-3 FORT MONMOUTH! NJ 07703	B TRI-TAC OFFICE ATTN: CSS (DR. PRITCHARD) 1 FORT MONMOUTH, NJ 07703	CDR, US ARMY RESEARCH OFFICE ATTN: DRXRO-TP PO BOX 12211 RESEARCH TRIANGLE PARK, NC 07709	CDR, US ARMY RESEARCH OFFICE ATTN: DRXRD-PH (DR. R. J. LONTZ) PO BOX 12211 RESEARCH TRIANGLE PARK, NC 27709	COMMANDANT US ARMY INST FOR MILITARY ASSISTANCE ATTN: ATSU-CTD-MO FURT BRAGG, NC 28307	CDR. US ARMY TROPIC TEST CENTER ATTN: STETC-MO-A (TECH LIBRARY) DRAHER 942 FORT CLAYTON, CANAL 70NE 09827	DIVISION CHIEF WETEOROLOGY DIVISION COUNTERFIRE DEPARTMENT FORT SILLA OK 73503
517	518	531	532	533	537	543

BEST AVAILABLE COPY

1 DRSEL-TL-DD 1 DRSEL-TL-DT *3 DRSEL-TL-3D 1 DRSEL-TL-3 1 DRSEL-TE 1 DRSEL-TE	**2 DRSEL-MS-TI 1 DRSEL-QG-TD 1 DRSEL-PP-I-PI 1 DRSEL-GS-H 1 DRSEL-CG (Mr. Doxey) 2 DRSEL-PA	1 DRSEL-RD 1 DRSEL-TL-D 1 USMC-LNO 1 TRADCC-LNO 25 Originating Office	700 CINDAS PURDUE INDUSTRIAL RESEARCH PARK 2595 YEAGER RDAD 001 W. LAFAYETTE, IN 47096	701 MIT - LINCOLN LABORATORY ATTN: LIBRARY (RM A-082) PO BOX 73 002 LEXINGTON, MA 02173	703 NASA SCIENTIFIC & TECH INFO FACILITY BALTIMORE/WASHINGTON INTL AIRPORT 001 PO BOX 8757, MD 21240	本 for number appetited in contract, and corners was a year.
E &	SION LABORATORY S COMMAND 2060	COMMAND RANGER NM 88002	ECTRONIC WARFARE E LAB. ECOM LE RANGE. NM 83002	V & SUPPORT OFC E LAB, ECOM 755	CS CDMMAND 703	
COMMANDER US ARMY LOGISTICS CENTER ATTN: ATCL-MC FORT LEE, VA 22801	DIRECTOR, NIGHT VISION US ARMY ELECTRONICS CO ATTN: DRSEL-NY-D FORT BELVOIR, VA 22060	CDR/DIR* ATMOSPHERIC S US ARMY ELECTRONICS CO ATTN: DRSEL-BL-SY-S WHITE SANDS MISSILE RA	CHIEF OFC OF MISSILE ELECTRO ELECTRONIC WARFARE LAB WHITE SANDS MISSILE RA	CHIEF INTEL MATERIEL DEV 8 S ELECTRONIC MARFARE LAB FORT MEADE, MD 20755	TRONI HA NJ	DRSEL-ML-D DRSEL-ML-D DRSEL-VL-D DRSEL-CT-D DRSEL-CT-D
572	602	603	604	606	680	

Dr. J.	Fairchi
S	
STANDARDS	
10	11
BUREAU	5. RM A-311
_	5

BLDG 225, RM A-331 ATTN: MR. LEEDY WASHINGTON, DC 20231 NATIONAL 704 001 ADVISORY GROUP ON ELECTRON DEVICES 201 VARICK STREET, 9TH FLOOR NEW YORK, NY 10014 705

ATTN: SECY, WORKING GROUP D (LASERS) ADVISORY GROUP ON ELECTRON DEVICES 106 005

201 VARICK STREET NEW YORK, NY 10014

005

BATTELLE MEMORIAL INSTITUTE 505 KING ÄVENUE TACTEC 707

COLUMBUS, OH 43201

001

PLASTICS TECH EVAL CENTER PICATINNY ARSENAL, BLDG 176 ATTN: MR. A. M. ANZALONE 602

DUVER. NJ OTBUI 100

ATTN: MR. FREDERICK LEUPPERT 1400 WILSON BLVD, ARCHITECT BLDG ARLINGTON, VA 22209 KETRON, INC. 710

METALS AND CERAMICS INF CENTER 711

BATTELLE

COLUMBUS, OH 43201 505 KING AVENUE 100

ild Consumer Products Div. 4001 Miranda Ave. Palo Alto, CA 94304 Castellano

001

002